



URSA PUREONE SF 31



/EU/ MW-EN 13162-T2-DS(70,-)-MU1-AFr20
/DE/ Anwendungsgebiete nach DIN 4108-10: DZ,DI,DAD-dk,WH,WTR
Bemessungswert der Wärmeleitfähigkeit nach DIN 4108-4: 0,032 [W/(m*K)]
Nicht brennbar, Baustoff glimmt nicht
Frei nach GefStoffV, ChemVerbotsV und EU-Richtlinie 1272/2008 (Anm. Q)
/CZ/ Univerzální tepelně izolační plst' z minerální vlny (MW)
Neobsahuje škodlivé látky ve smyslu směrnice 97/69/ES (Pozn.Q)
/AT/ Anwendungstyp MW-WL nach ÖNORM B6000
/SI/ Steklena volna - zakon o gradbenih proizvodih
/PL/ Maty z wełny mineralnej. Izolacja cieplna w budownictwie
/IT/ Lana Minerale per Isolamento Termico ed Acustico in Edilizia



PUREONE SF 31
DoP-No: 49UPO31NRN19021
<https://dop.ursa.com>
EN 13162:2012+A1:2015
Factory made mineral wool (MW) products
Thermal Insulation for Buildings
T2-DS(70,-)-MU1-AFr20

2141395



4 017916 512394

Thickness [mm]

120

Length [mm] Width[mm]

3200x1200

Piece(s)

1

Surface [m²]

3,842

1524210702

V-8A01-L1



Thickness d _N [mm]	120
Thermal conductivity λ _D [W/(m*K)]	0,031
Thermal resistance coefficient R _D [m ² *K/W]	3,85
Reaction to fire (RtF)	A1

URSA Deutschland GmbH www.ursa.de
Carl-Friedrich-Benz-Str. 46-48, 04509 Delitzsch